AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client: Beaulieu of Australia Limited

166 Pearson Road Yatala QLD 4207 **Test Number** : 20-003813

Issue Date : 3/09/2020 Print Date : 3/09/2020

Order Number: 32887

Sample Description Clients Ref : "Mirror Image"

Loop pile carpet tested on Dunlop Government Red Underlay

Colour : Black & Grey End Use : Flooring

Nominal Composition: 100% Resistain Solution Dyed Nylon

Nominal Mass per Unit Area/Density: 28oz/yd2

AS ISO 9239.1-2003 R

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a

Radiant Heat Source

Date of Sample Arrival 30/07/2020
Date Tested 02/09/2020

CHF Value	1	2	3	Mean
Length	3.3	3.0	3.4	3.2 kW/m²
Width	3.4	-	-	- kW/m²
HF-30 Value	1	2	3	Mean
Length	3.3	3.4	-	- kW/m²
Width	3.5	-	-	- kW/m²
Smoke Value	1	2	3	Mean
Length	125	125	136	129 %.min
Width	139	-	-	- %.min

Melting

Penetration of flame through to substrate

Yes

213589 45674 Page 1 of 2

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing
- Mechanical Testing

Performance & Approvals Testing

: Accreditation No. 983 : Accreditation No. 985 : Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



MICHAEL A. JACKSON B.Sc.(Hons)

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client: Beaulieu of Australia Limited

> 166 Pearson Road Yatala QLD 4207

Test Number : 20-003813

Issue Date 3/09/2020 3/09/2020 **Print Date** Order Number: 32887

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

HF30 not reported as flame out time occurred before 30 minutes.

Each specimen was loose laid over Dunlop Government Red underlay and 6mm thick fibre reinforced cement board and clamped prior to testing.

213589 45674 Page 2 of 2

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing

- Mechanical Testing

- Performance & Approvals Testing

: Accreditation No. : Accreditation No

985 : Accreditation No 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

> HAEL A. JACKSON B.Sc.(Hons) ANAGING DIRECTOR